

NW1926

Fasson® Direct-Therm Synthetic Paper/AP104/BG40# WH imp

Fasson® Direct-Therm Synthetic Paper is a smooth white polypropylene film with a thermo sensitive layer laminated

Applications





Key Features

> Low speed barcode thermal printing.

NW1926

Fasson® Direct-Therm Synthetic Paper/AP104/BG40# WH imp





Facestock

Direct-Therm Synthetic Paper is a smooth white polypropylene film with a thermo sensitive layer laminated

Basis Weight: 60 g/m2± 10% ISO536

Caliper: 0.075 mm ± 10% ISO534

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

A super calendared white glassine paper, with excellent roll label converting properties.

Basis Weight: 60 g/m2 10% ISO536

Caliper: 0.055mm 10% ISO534

Performance data

Loop Tack (st,st)-FTM 9: 14.0 or Tear

20 min 90 Peel (st,st)-FTM 2: 7.0 or Tear

24 hour 90 Peel (st,st)-FTM 2: 8.0 or Tear

Minimum Application Temperature: +7C

After Labeling 24Hours,Service Temperature Range: -50C~+90C

Adhesive Performance

This is a clear, general purpose permanent adhesive with good initial tack and ultimate adhesion to a wide variety of substrates. Designed exclusively for industrial labeling applications. This adhesive is suitable for applications where compliance with FDA 175.105 is required. This section covers applications where for indirect or incidental contact food, cosmetic or drug products..

Applications and use

This thermo sensitive product is designed for low speed barcode thermal printing. Darkness of printing is recommended to middle grade. For example, Zebra 140Xill plus' darkness is advise to set as 15~20 This product is suit for use in airport luggage tag or some logistic label. It has a special low ion top coating providing protection for the thermal layer to prevent damage of water and rubbing during the transportation. It is recommended to consume the material in 3 months after receiving them. Storage environments that will be prolonged exposure to sunshine or above 50° C should be avoided. The above does not represent any guarantee or warranty and the Purchaser must independently determine the suitability of the products for the Purchaser's purposes.

Conversion/printing

This product is suited for all the usual printing technologies. Due to the thermal sensibility, in the process material temperature should not more than 50℃. Solvent may cause damage to surface coating. Care should be taken when using solvent based inks. Ink testing is always recommended before production.

SHELF LIFE

One year when stored at 23±2℃ at 50±5%RH.

Asia Pacific
32/F., Skyline Tower
39 Wang Kwong Road
Kowloon Bay, Kowloon,
Hong Kong
Tel: +852 2802-9618

Warrenty
All statements, technical information and recommendations about AVERY DENNISON products are based upon tests believed to be reliable but but do no constitute a guarantee or warranty. All AVERY DENNISON products are sold with the understanding that PURCHASER has independently determined the suitability of such products for its purposes. AVERY DENNISON products are warranted to be free of defects in material or workmanship for a period of one year from the date of shipment. Any product shown to the satisfaction of AVERY DENNISON within the time provided to be so defective shall be replaced without charge of AVERY DENNISON may issue credit in such amount as it seems reasonable however, in no event shall AVERY DENNISON be responsable for claims beyond the replacement value of the defective product or in any way liable or responsable for consequential or incidental damages. NO EXPRESS WARRANTIES, WHETHER OF MERCHANTIBILITY OR FITNESS FOR ANY ARTICULAR USE, OR OTHERWISE, EXCEPT AS SET FORTH ABOVE (WHICH IS MADE EXPRESSLY IN LIEU OF ALL OTHER WARRANTIES) SHALL APPLY TO PRODUCTS SOLD BY AVERY DENNISON. AVERY DENNISON SPECIFICALLY DISCLAIMS AND EXCLUDES ALL OTHER SUCH WARRANTIES. NO WAIVER, ALTERNATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND SIGNED BY AN EXECUTIVE OFFICER OF AVERY DENNISON. No salesman, representative, or agent of AVERY DENNISON is authorized to give any guarantee, warranty or make any representation contrary to the above.